

STERISHEET STERILIZATION WRAPS

STERISHEET 355 SMS



DESCRIPTION

Sterisheet sterilization wraps are best in class Sterile Barrier Systems for CSSDs in hospitals and clinics. Sterisheet SMS products are available as interleaved, bonded or single sheets.


COMPOSITION

100% synthetic fibers made of polypropylene.

Spunbond / Meltblown / Spunbond

Spunbond network consist of long, strong and thick polypropylene filaments.

Meltblown layers are made of short and thin polypropylene microfibers.



SUITABLE FOR STERILIZATION METHODS

- Steam
- EO
- Plasma

APPLICATION

For medium-size and heavy trays and instrument kits.

SIZES AVAILABLE

Choose standard sizes to optimize your costs.

Other sizes are also available upon request.

60x60 cm 100x100 cm

75x75 cm 120x120 cm

90x90 cm 137x137 cm

STERISHEET STERILIZATION WRAPS

STERISHEET 355 SMS



COLORS



PERFORMANCES

Mechanical and bacterial barrier properties are internally tested on a routine basis according to regulatory requirements of all of our products. Combining them with random tests conducted by external and accredited laboratories leads Sterimed to secure the best performances on Sterisheet products.

Mechanical Properties

Preservation of pack integrity from closure till the point of use depends on the materials resistance to tearing, puncturing and breaching stresses generated all along the distribution with the hospital. Any mechanical weaknesses will increase the risks of event related ingress of microorganism into the pack.

Excellent mechanical properties will provide you additional safety while using our materials. Optimal strength and resistance provided in every sheet.

Bacterial Properties

Sterilization wraps must prevent microorganisms' ingress inside the package.

To reach this performance, different types of testing have to be performed on the products to reproduce both kind of ingress vehicles possible:

- Airborne ingress
- Waterborne ingress

For instance, according to the TNO final pack test method, validating the materials & the folding technique, STERISHEET 355 SMS exhibits a BARRIER PROTECTION > 99,99%

STERISHEET 355 SMS	
PROPERTIES	TYPICAL
Basis Weight	55 g/m ²
Air permeability	90 l/min/dm ²
Thickness	385 µm
Hydrost Test	45 mBar
Tensile strength SM	2.4 kN/m
Tensile strength ST	1.1 kN/m
Elongation SM	55 %
Elongation ST	55 %
Burst	260 kPa
Tears SM	8000 mN
Tears ST	10000 mN

STERISHEET STERILIZATION WRAPS

STERISHEET 355 SMS



COMPLIANCE TO STANDARDS

Sterisheet products range is classified as a Class I Medical Device according to the European Medical Device Directive (MDD). Its CE marking illustrates the relevant compliance.

Sterisheet products conform with the standards below:

EN ISO 11607-1:2017

EN 868-2:2017

OUR WRAPS MANUFACTURING THIRD PART CERTIFICATION

ISO 13485 standards

PACKAGING PRIOR TO USE

Sheets display is optimized by adjusted folding depending on the size and type of the product. We have carefully tested the best solution to ensure the most convenient handling for end users.

- PRIMARY TRANSPORT PACKAGING

Number of sheets is maximized and wrapped in transparent polyethylene bag with quick product ID.

- SECONDARY TRANSPORT PACKAGING

Secondary packaging is a neutral brown color cardboard box providing transportation stress resistance.

LABELLING

Product traceability is fully insured through labelling according regulations on each transport packaging.

STORAGE CONDITIONS

Sterimed recommends the following storage conditions for best performance of sterilization wraps: Storage in a cool, dry location away from direct exposure to natural light, strong artificial light & UV sources.

STERISHEET STERILIZATION WRAPS

STERISHEET 355 SMS



Cardboard boxes should never be stored in direct contact with the floor. Storage of the products shall be done in areas that are not subject to extreme temperature changes such as in contact with heated objects, vents or cold walls. As per AAMI ST79 “*Comprehensive guide to steam sterilization and sterility assurance in health care facilities*” recommendations: Before use, hold packaging materials at room temperature (20°C to 23°C) and at a relative humidity ranging from 30% to 60% for a minimum of 2 hours is a good practice for optimum use performances.

USE BY DATE

Provided the above storage conditions are met, the upper limit of the time interval during which the performance characteristics of the sterile barrier system are demonstrated is 5 years of the manufacturing date.

ENVIRONMENTAL IMPACT & WASTE MANAGEMENT

Oil derived product, renewable content 0%.

Disposal as per local regulations after use.